



ABSTRACT

A capsule curing agent including a core containing an amine curing agent (A) and a capsule membrane covering the core, wherein the capsule membrane has a bonding group (x) absorbing infrared rays of a wave-number of 1630 to 1680 cm^{-1} and/or a bonding group (y) absorbing infrared rays of a wave-number of 1680 to 1725 cm^{-1} , and contains cured material of an epoxy resin cured by the amine curing agent (A) as a curing agent, and a weight ratio of the core to the capsule membrane is from $100:1$ to $100:100$.